

Molded Polystyrene Insulation.

Tru-R molded polystyrene insulation is a cost effective, durable, and energy efficient solution for all types of insulation applications. Tru-R Insulation is an insulation manufactured to provide architects, specifiers, distributors, and contractors all the features and benefits inherent in a quality insulation.

R-value - Tru-R 50 has an R-value that never changes over time.

Strength - Tru-R 50 has a compressive strength of 5 psi.

Moisture Resistance - Tru-R 50 is a closed cell polystyrene insulation and is resistant to moisture gain.

Vapor Permeable - Tru-R 50 allows moisture vapor to move through its structure.

Drying Potential - Tru-R 50 rapidly releases absorbed moisture.

Applications.


- Precast Concrete Core
- Void Fill
- Flotation
- Protective Packaging

Proven to meet, or exceed, building codes.

Tru-R insulation is manufactured under an industry leading quality control program monitored by UL and further recognized in UL Evaluation Report UL ER40266-01.



Tru-R insulation meets Type XI of ASTM C578, "Standard Specification for Rigid, Cellular Polystyrene Thermal Insulation".

		
Compressive Strength ^{1,2} @ 10% deformation, min. ASTM D1621	psi (kPa)	5 (35)
R-value ¹ , Thermal Resistance, per inch, ASTM C518	25°F	°F·ft ² ·h/Btu (°K·m ² /W) 3.6 (0.63)
	40°F	°F·ft ² ·h/Btu (°K·m ² /W) 3.4 (0.60)
	75°F	°F·ft ² ·h/Btu (°K·m ² /W) 3.2 (0.56)
k-value Thermal Conductivity ASTM C518	25°F	Btu·in/°F·ft ² ·h (W/°K·m) 0.28 (0.040)
	40°F	Btu·in/°F·ft ² ·h (W/°K·m) 0.29 (0.042)
	75°F	Btu·in/°F·ft ² ·h (W/°K·m) 0.31 (0.045)
Density, Nominal ASTM C303	lb/ft ³ (kg/m ³)	0.75 (12)
Flexural Strength ¹ , min. ASTM C203	psi (kPa)	10 (69)
Water Vapor Permeance ¹ of 1.0 in. thickness, max., perm ASTM E96		5.0
Water Absorption ³ , volume % ASTM C272		0.3
Flame Spread Index ASTM E84		<25
Smoke Developed Index ASTM E84		<450
Maximum long-term use temperature		165°F (74°C)
ASTM C578 Compliance, Type		XI

¹ Please refer to ASTM C578 specification for complete information.

² Compressive strength is measured at 10 percent in accordance with ASTM C578. A safety factor is required to prevent long-term creep for sustained loads. For static loads, a safety factor of 3:1 is recommended.

³ ASTM C272 24 hour immersion followed by 24 hour storage in 75°F/50%RH air.